




APPENDIX E
TECHNICAL SCHEDULE OF COLUMNS

| ITEM | DESCRIPTION | DATA |
|------|--|--|
| 1. | COLUMN | RV100FA |
| a. | Name of manufacturer | LYSAGHT GALVANIZED STEEL BHD |
| b. | Address & country of manufacturer / fabricator of column | MEDAN TASEK, KAWASAN PERINDUSTRIAN TASEK, IPOH |
| c. | Type of column *Delete whichever not applicable | Hot-Dipped Galvanized Steel / * Pre-Stressed Spun Concrete / * Fibreglass Reinforced Type 1 / Type 2* Others.* |
| d. | Compliance with relevant section of *Delete whichever not applicable | BS 5649 (EN40)* ANSI C-136.20 & ASTM D-4923-89* Others (Specify)* |
| e. | Name of hot-dip galvanizing company | LYSAGHT GALVANIZED STEEL BHD |
| f. | Address & country of manufacturer of steel coils | NIPPON STEEL & SUMITOMO METAL CORPORATION 1, NISHINOSU, OITA-CITY, OITA-PREF., 870-0992, JAPAN |
| g. | Galvanizing standards & minimum weight per m ² (g/m ²) | BS EN ISO 1461 / 460 g/m ² |
| h. | Overall height of column (m) | 10 m |
| i. | Tapering ratio | 13 / 14 APPROX. |
| j. | Weight of column (kg)-Whole Upper section Lower section | 107 kg APPROX. 55 kg APPROX. 52 kg APPROX. |
| k. | Thickness of steel column (mm) / Concrete wall thickness (mm) | MIN. 2.5 thk NOT APPLICABLE |
| l. | Name of company applying bituminous paint | NOT APPLICABLE |
| m. | Address of company applying bituminous paint | NOT APPLICABLE |
| n. | Dry film thickness of bituminous paint (mm) | NOT APPLICABLE |
| o. | Equivalent weight of bituminous coating per sq.m (g/m ²) | NOT APPLICABLE |
| p. | Longitudinal seam weld minimum penetration (%) | 60 % |
| q. | Reference standard of welding test (Latest relevant B.S.) | BS EN 1011-2 |

Lin Sita

T/t, Nama & Cop Pengilang



T/t, Nama & Cop Kontraktor Elektrik

APPENDIX E

...cont. pg. 46/49